

TECHNICAL SHEET FOR ALUMINUM SCRAP

**TAINT TABOR**



Statement of compliance	Industrial standard	Quantity	Processing	Logistic and density conditions
Regulation no. 333/2011	13920-06	22 tonnes	Shredded	Bulk

**CHARACTERISTICS**

Size	Impurities	Metal yield
50-200 mm	2%	>90%

**CHEMICAL COMPOSITION**

Element	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Pb	Sn
Sample 1	0.4728	0.3279	0.1404	0.3275	0.4624	0.0114	0.0083	0.0326	0.0222	0.0031	0.0000
Sample 2	0.4505	0.3055	0.1330	0.3217	0.4695	0.0110	0.0077	0.0322	0.0213	0.0030	0.0001
Sample 3	0.4799	0.3384	0.1515	0.3356	0.4518	0.0116	0.0086	0.0325	0.0219	0.0034	0.0000
<b>Average</b>	<b>0.4677</b>	<b>0.3239</b>	<b>0.1416</b>	<b>0.3283</b>	<b>0.4612</b>	<b>0.0113</b>	<b>0.0082</b>	<b>0.0324</b>	<b>0.0218</b>	<b>0.0032</b>	<b>0.0000</b>