

**TECHNICAL SHEET ALUMINUM SCRAP**

*Al-Mg*



| Quality conditions of delivery | Industrial standard | Quantity  | Processing | Logistic and density conditions |
|--------------------------------|---------------------|-----------|------------|---------------------------------|
| Regulation no. 333/2011        | 13920-5             | 20 tonnes | Shredded   | Bulk                            |

**CHARACTERISTICS**

| Impurities | Metal yield |
|------------|-------------|
| 0 %        | min 95 %    |

**CHEMICAL COMPOSITION**

| Element | Si     | Fe     | Cu     | Mn     | Mg     | Cr     | Ni     | Zn     | Ti     | Pb     | Sn     |
|---------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|--------|
| %       | 0.6014 | 0.3256 | 0.0221 | 0.2015 | 3.0981 | 0.0373 | 0.0000 | 0.0650 | 0.0171 | 0.0000 | 0.0000 |
| %       | 0.5984 | 0.4129 | 0.0341 | 0.2834 | 2.7059 | 0.0418 | 0.0020 | 0.0540 | 0.0182 | 0.0000 | 0.0000 |