

Al pentru dezoxidare

Compozitie (%)	Al	Si	Fe	Cu	Mn	Mg	Zn	Pb
Al 95%	min 95	max 2	max 1.5	max 1	max 0.5	max 1	max 1	
Al 96%	min 96	max 1		max 0.5	max 0.7	max 1.2	max 0.5	max 0.1
Al 97%	min 97	max 1	max 2					